

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: D06M 13/432, 16/00, A01N 47/44, C07C 279/26	A1	(11) International Publication Number: WO 95/12021 (43) International Publication Date: 4 May 1995 (04.05.95)
(21) International Application Number: PCT/GB94/02184 (22) International Filing Date: 7 October 1994 (07.10.94) (30) Priority Data: 9322132.3 27 October 1993 (27.10.93) GB (71) Applicant (for all designated States except US): ZENECA LIMITED [GB/GB]; 15 Stanhope Gate, London W1Y 6LN (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): PAYNE, John, David [GB/GB]; 5 Hargreaves Court, Lumb, Rossendale EB4 9QA (GB). (74) Agents: PUGSLEY, Roger, Graham et al.; Intellectual Property Group, Zeneca Specialties, P.O. Box 42, Hexagon House, Blackley, Manchester M9 8ZS (GB).	(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LT, LU, LV, MD, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ). Published <i>With international search report.</i>	
(54) Title: ANTIMICROBIAL TREATMENT OF TEXTILE MATERIALS (57) Abstract Antimicrobial treatment of textile material with an oligomeric or polymeric biguanide and a strong organic acid having a pK value below 4.5. Acid protects treated material against yellowing in the presence of chlorine bleaches and loss of antimicrobial activity on laundering. The preferred biguanide is poly(hexamethylene biguanide) hydrochloride.		

ANTIMICROBIAL TREATMENT OF TEXTILE MATERIALS

The present invention relates to textile materials which are treated with a biguanide and a strong organic acid to prevent yellowing and loss of antimicrobial activity when subsequently laundered with an anionic detergent containing hypochlorite bleach.


5 It has been proposed to treat textile materials with poly(hexamethylene biguanide) in order to confer antimicrobial properties to the textile material as disclosed in EP 136 900.

Biguanides are particularly suited to application to textiles, especially cellulosic textiles and blends thereof, because of the substantivity which biguanides exhibit for such materials. However, such applications have not become commercially established where the treated material is to be subjected to laundering. There are two major reasons for this. Firstly, many commercially available detergents contain chlorine bleaching agents which react with the biguanide groups to produce a yellow discoloration and cause loss of antimicrobial protection. This is a particular disadvantage in white or pale coloured textiles. Secondly, many commercial detergents contain anionic surfactants which complex with the biguanide groups which often produce sticky deposits resulting in loss of "handle" and often impair the stain-release properties of the textile material. Also, following laundering, the textile material often exhibits an increase tendency to "tendering".

It has now been found that some or all of these deficiencies may be overcome by treating the textile material with a biguanide and an organic acid.

According to the invention, there is provided a method of treating a textile material to inhibit microbial growth which comprises applying to the textile material a) an oligo- or polymeric biguanide or the salt thereof with an inorganic acid or an organic acid having a pK value above 4.5 (hereafter "biguanide") and b) a strong organic acid having a pK value below 4.5 and free from any aliphatic or oxyalkylene chain containing 12 or more carbon atoms (hereafter "strong organic acid").

The biguanide which is used to treat the textile material contains at least two biguanide units of the formula (I):-



and preferably from 2 to 100 such biguanide units.

Typically the biguanide units are linked by a bridging group which includes at least one methylene group. The bridging group may

include a polymethylene chain which may optionally be interrupted by hetero atoms such as oxygen, sulphur or nitrogen. The bridging group may include one or more cyclic nuclei which may be saturated or unsaturated. It is generally preferred that the bridging group is such that there are at least three, and especially at least four, carbon atoms directly interposed between adjacent units of the formula (I). In general it is preferred that there are not more than ten carbon atoms and, especially not more than eight carbon atoms interposed between two adjacent units of the formula (I).


The terminal biguanide units may themselves be terminated by any suitable terminating group such as hydrocarbyl, substituted hydrocarbyl group, amino or amine hydrochloride or a group -NH-C-NH-CN

NH


If the terminating group is hydrocarbyl this may be alkyl, cycloalkyl or aryl or a combination thereof, such as aralkyl. If the terminating group is substituted hydrocarbyl, the substituent or substituents can be any group or groups which do not have an undesirable adverse effect on the antimicrobial activity of the biguanide such as a hydrocarbyloxy, hydrocarbylcarbonyl (i.e. acyl), an ester (i.e. acyloxy), halogen atom or CN.

The biguanide may comprise a single species, especially where this is a dimer, or a mixture of species especially where it is polymeric and comprises a mixture of polymers having different chain lengths.


One preferred biguanide is a dimer which contains two units of the formula (I) linked by a polymethylene group, particularly a hexamethylene group. The terminating groups of preferred dimers are



4-chlorophenyl or 2-ethylhexyl, for example as in the compound of formulae (IIa) and IIb, respectively



Another preferred biguanide comprises a mixture of polymeric biguanides, especially a mixture of linear polymeric biguanides with a recurring polymer unit represented by the formula



wherein X and Y may be the same or different and represent bridging groups in which the total number of carbon atoms directly interposed between the pairs of nitrogen atoms linked by X and Y is at least 9 and not more than 17.

The bridging groups X and Y may be polymethylene chains, optionally interrupted by hetero atoms such as oxygen, sulphur or nitrogen. X and Y may also incorporate cyclic nuclei which may be saturated or unsaturated, in which case the number of carbon atoms directly interposed between the pairs of nitrogen atoms linked by X and Y is taken as including the shortest segment or segments of the cyclic group or groups. Thus, the number of carbon atoms directly interposed between the nitrogen atoms in the group





The preferred biguanide for use in the present invention is poly(hexamethylene biguanide), in which X and Y both represent the $-(\text{CH}_2)_6-$ group.

The mixture of polymeric biguanides may be prepared by the methods described in UK Patent Specification Nos. 702,268 and 1,152,243 respectively, and any of the biguanide species or mixtures thereof described therein may be used as the biguanide in the present invention.


The polymeric biguanides may be terminated by an amine hydrochloride group or by an $-\text{NH}-\text{C}-\text{NH}-\text{CN}$ group, and the terminating groups on each polymer chain may be the same or different.

In any mixture of polymeric biguanides the number of individual biguanide units, i.e.



is preferably from 3 to about 80.

A preferred biguanide is a mixture of poly(hexamethylene biguanides) of formula III in the form of their hydrochloride salts.



wherein n is from 4 to 15. The average molecular weight of this mixture of polymeric biguanides is from about 1100 to about 3300.

10 A preferred mixture of polymeric biguanides is available as an aqueous concentrate supplied as VANTOCIL IB (ZENECA Ltd). Poly(hexamethylene biguanide) hydrochloride is hereinafter referred to as PHMB.

15 The biguanide is preferably applied to the textile material as a salt of an inorganic acid or weak organic acid having a pK value above 4.5 (hereafter "weak organic acid"), especially a monobasic inorganic or weak organic acid. Examples of inorganic acids are hydrohalic acids such as the hydrobromic acid and especially hydrochloric acid. Examples of weak organic acids are acetic and propionic acids.

20 The strong organic acid may itself have antimicrobial activity, but this is not essential to the working of the invention. It may be a sulphonic acid or a sulphate but is preferably a carboxylic acid. The organic acid may contain more than one acid group such as in di- and tri-carboxylic acids and polymers and co-polymers derived from acrylic and methacrylic acid.

25 The strong organic acid may be substituted or unsubstituted. When it is substituted, the substituent or substituents may be any atom or group which reduces the pK value relative to the unsubstituted acid provided that such atom or group does not significantly affect the antimicrobial properties of the treated textile material and that it provides the required resistance to laundering. In the context of the invention, sulphamic acid is to be regarded as a strong organic acid.


Preferred strong organic acids are those containing 2 or 3 carboxylic acid groups.

35 The strong organic acid is essentially devoid of surface active properties and has little or no detergency properties. It is also essentially non-foaming.

The strong organic acid preferably has a pK value less than 4.0, more preferably less than 3.5 and especially from 3.1 to 0.5.

40 The acid group or groups of the strong organic acid are preferably -COOH, -CSOH or -COSH although in the following generic formulae IV, V and VI such groups are represented as -COOH for convenience. It is preferred that each acidic group is carboxy i.e. -COOH.

One preferred strong organic acid has the formula IV




wherein

R is halogen, C₁₋₆-alkyl, C₁₋₆-alkenyl, substituted C₁₋₆-alkyl, phenyl, substituted phenyl, nitrile, carboxy, a group OR³ or a group R³CO.

R¹ and R² are, independently, hydrogen, halogen, amino, substituted amino, hydroxy, C₁₋₆-alkyl, substituted C₁₋₆-alkyl or R and R¹ together with the carbon atom to which they are attached form an alicyclic or heterocyclic ring; and

R³ is C₁₋₆-alkyl, substituted C₁₋₆-alkyl, phenyl or substituted phenyl; provided that R, R¹ and R² are selected to give a pK value below 4.5.

Another preferred strong organic acid has the formula V




wherein

R⁴ is hydrogen, C₁₋₆-alkyl, substituted C₁₋₆-alkyl, C₁₋₆-alkenyl, phenyl substituted phenyl or -COOH; and

R⁵ and R⁶ are, independently, hydrogen, C₁₋₄-alkyl or substituted C₁₋₄-alkyl.

A further preferred strong organic acid has formula VI



wherein

R⁷ is phenyl, substituted phenyl or the group -COOH.

When R, R¹ or R² is halogen, it is preferably iodine, fluorine, bromine or more especially chlorine.

When R, R¹, R² or R³ is alkyl, it may be linear or branched, but is preferably linear.

When R to R⁶ is substituted alkyl, the substituent or substituents is preferably hydroxy, halogen, amino, substituted amino, nitrile, carboxy or R⁸CO- where R⁸ is C₁₋₄-alkyl or phenyl.

When R¹ or R² is substituted amino, the substituent is preferably C₁₋₄-alkyl or the group R⁸-CO.

When R, R³, R⁴ or R⁷ is substituted phenyl, the substituent is preferably C₁₋₄-alkyl, hydroxy, halogen, nitro or -COOH.

When R and R¹ together with the carbon atom to which they are attached form an alicyclic ring, it is preferably cyclohexyl or cyclopropyl.

When R and R¹ together with the carbon atom to which they are attached form a heterocyclic ring, it is preferably furanyl.

Examples of the strong organic acid of formula IV wherein R¹ is amino or substituted amino are aspartic acid, leucine, phenylalanine and hippuric acid.

Organic acids of formula IV which have been found particularly useful are those containing two or more carboxylic acid groups, especially those also containing one or two hydroxy groups i.e. wherein one or both of R¹ and R² is hydroxy. Examples of such acids are adipic, butane tetracarboxylic, citric, dihydroxymalic, dihydroxytartaric, dimethylmalic, dimethylmalonic, glutaric, itaconic, malic, malonic, methylglutaric, methylmalonic, methylsuccinic, suberic, succinic, tartronic and tartaric acid.

Examples of monocarboxylic organic acids of formula IV are acetoacetic, ascorbic, bromoacetic, chloroacetic, chlorobutyric, chlorophenoxyacetic, chlorophenylacetic, chloropropionic, cyanoacetic, cyanophenoxyacetic, cyanopropionic, dichloroacetic, dichloroacetylacetic, diphenylacetic, ethylphenylacetic, glycolic, hydroxypropionic, iodoacetic, lactic, mandelic, nitrophenylacetic, nitrophenylpropionic, phenylacetic, phenylpropionic, trichloroacetic and vinylacetic acid.

Examples of organic acids of formula IV where R and R¹ form an alicyclic ring are cyclohexane-1,1-dicarboxylic and cyclopropane-1,1-dicarboxylic acids.

Examples of organic acids of formula V are acrylic, chlorocinnamic, fumaric, maleic, mesaconic, methylcinnamic and sorbic acid.

Examples of acids of formula VI are benzoic, bromobenzoic, chlorobenzoic, dihydroxybenzoic, ethylbenzoic, hydroxybenzoic, iodobenzoic, trimethylbenzoic, o-phenylbenzoic, phthalic, isopropylbenzoic, terephthalic, toluic acid and oxalic acid.

Examples of thiocarboxylic acids are thioacetic, thiomalic, thioglycolic and thiolactic acids.

Particularly useful effects have been obtained with citric, maleic, malonic and especially oxalic acids.

The textile material may be of natural or synthetic fibres including blends thereof. Thus, it may be cellulose, including viscose rayon and regenerated viscose rayon, wool, acrylic, polyamide such as nylon, polyester such as polyethyleneglycolterephthalate or polyurethane. It is, however, preferably cellulose or blends thereof.

The textile material may be woven or knitted or may be in the form of dry or wet laid fibres. It may be in the form of sheets, webs, threads or ready made up garments such as drapes, shirting, toweling, underwear, socks and sheeting. The textile material is especially that

which may become soiled and prevalent to microbiological growth thus giving rise to objectionable odours or to health/hygiene problems.

The biguanide may be the only antimicrobial agent applied to the textile material or a mixture of such biguanides may be used. Other antimicrobial agents may also be included to improve the spectrum of microbiological protection provided that such other antimicrobial agent does not significantly interfere with the improved resistance of the treated textile material to laundering.

The textile material may also contain other textile processing adjuvants such as binders or resins, especially phenol-formaldehyde or urea-glyoxal resins which are commonly used in the trade to impart crease-resistance and "easy care" properties to the textile material.

The biguanide is preferably applied to the textile material before the strong organic acid is applied. The biguanide and strong organic acid may be applied by any process common to the textile industry which is appropriate to the actual textile material. Thus, application may be by batch or substantive exhaustion, padding, dipping or spraying. Where appropriate, the textile material may be dried after application of the biguanide and prior to the application of the strong organic acid. The textile material may be white or coloured with either dyestuffs or pigments. It may contain other textile adjuvants commonly used in textile finishing processes such as brightening agents and softeners.

Since the biguanide in the form of a salt with an inorganic acid or weak organic acid is water soluble, the biguanide is preferably applied from aqueous solution. However, the solution of biguanide may contain other hydrophilic compounds or co-solvents such as ethanol. Similarly, the strong organic acid is also preferably applied from aqueous solution either in the form of the free carboxylic acid or in the form of a water-soluble salt, especially alkali metal salt such as lithium, sodium or potassium salt or as an ammonium salt.

The amount of biguanide which is applied to the textile material may be just sufficient to confer an antimicrobial effect to the material but is preferably in excess of this amount. Generally, the amount of biguanide is up to 2% preferably up to 1%, more preferably up to 0.5% and especially up to 0.1% by weight of the textile material. Good antimicrobial effects have been obtained with up to 0.01% by weight of textile material.

For convenience, an excess of the strong organic acid is applied so that those biguanide groups which are not required to bind with the textile material are blocked by the strong organic acid. Any excess of the acid may be removed by rinsing with water, but this is generally not necessary. It is particularly preferred that the amount

of strong organic acid is just sufficient to form a salt with all the biguanide groups not required to bind with the textile material.

The textile material containing the biguanide which has been treated with the strong organic acid shows reduced tendency to discolour when exposed to a chlorine-containing bleach and also retains antimicrobial activity after washing with an anionic detergent. It has been found that certain textile materials, especially cellulosic materials retain antimicrobiological activity even after repeated laundering cycles. In addition, the textile materials treated according to the invention retain similar "handle" and "soil- release" characteristics after laundering compared with that of the untreated material.

Thus, as a further aspect of the invention there is provided a textile material treated with an oligo- or polymeric biguanide and a strong organic acid having a pK value below 4.5 and free from any aliphatic or oxyalkylene chains containing more than 12 carbon atoms. Some of the salts formed on the textile material are believed novel. Thus, as a still further aspect of the invention there is provided a salt of poly(hexamethylene biguanide) and a strong organic acid having a pK below 4.5 and free from any aliphatic or oxyalkylene chains containing more than 12 carbon atoms.

The invention is now further described with reference to the following examples where the amounts are expressed as parts by weight unless expressed to the contrary.

25

Examples 1 to 17

These examples illustrate the protection against yellowing. 5 cm² squares of white cotton woven cloth (0.25 parts) were immersed in a 0.1% aqueous solution of PHMB for 5 minutes at 20-25°C. The cotton was then removed and rinsed thoroughly with water. The treated cotton was then immersed in a 1% aqueous solution of a strong organic acid for 5 minutes at 20-25°C and again removed, squeezed and rinsed with water. The cotton pieces were finally immersed in a 3% aqueous solution of sodium hypochlorite at 40°C for 1 hr. Again the cotton pieces were squeezed and thoroughly rinsed in water before drying.

The colour of these samples was assessed visually by measuring the colour with a Macbeth Reflectance Spectrophotometer. The results are given in Table 1 below.

40

TABLE 1

Example a Comp Ex	Organic Acid	pK	Whiteness (a) %
1	citric	2.9	100
2	lactic	3.7	97.0
3	glycolic	3.6	98.7
4	thioglycolic	3.4	99.9
5	thiolactic	3.5	99.6
6	ethoxyacetic	3.5	98.5
7	chloroacetic	2.7	101.9
8	tartaric	2.8	98.9
9	malic	3.2	97.6
10	benzoic	4.0	ND
11	aspartic	1.9	90.0
12	phenylalanine	2.2	89.7
13	leucine	2.4	89.5
14	oxalic	1.1	100
15	malonic	2.6	99.3
16	maleic	1.7	96.8
17	btca	3.4	99.8
A	acetic	4.5	yellow
B	2-hydroxybutyric	4.7	yellow
C	3-hydroxybutyric	4.72	yellow
D	4-hydroxybutyric	4.72	yellow
E	boric		yellow
Control	-	-	73

Footnote to Table

btca is butane tetracarboxylic acid

a) Whiteness is measured as percent reflectance against a piece of untreated cotton.

ND is not determined.

Example 18

This illustrates the antimicrobial properties of treated cotton.

A phosphate buffer as prepared by mixing aqueous solutions of 0.2 mol/litre Na_2HPO_4 (72 ml) and 0.2 mol/litre NaH_2PO_4 (28 mls), adding

NaCl (5 parts) and diluting to 1 litre with distilled water. This buffer solution was sterilised by heating at 121°C for 15 minutes.

A 24 hour shaken culture of *Staphylococcus aureus* (ATCC 6538P) was prepared at 37°C. The cell concentration was measured using a haemocytometer and the culture diluted with the phosphate buffer solution to give a concentration of between 5E5 and 3E5 cfu/ml (E is logarithmic power to base 10).

Samples of cotton cloth (0.2 parts) to be tested were placed in a screw-necked flask, inoculated with 0.2 ml of the bacterial culture, and the flask sealed and incubated at 37°C for 18 hours.

After incubation, 20 mls of the phosphate buffer solution were added and the flask shaken for about 1 minute. The concentration of surviving cells in the buffer solution was then determined by a standard serial dilution technique on nutrient agar after 24 hour incubation at 37°C. The results are detailed in Table 2 for cotton samples treated with citric acid alone, PHMB alone and both citric acid and PHMB both with and without bleach. The treatment with citric acid, PHMB and bleach is as described in Example 1. The results show that citric acid prevents yellowing but exhibits poor antimicrobial activity and that the combination of citric acid and PHMB retains antimicrobial activity and also protects against yellow discoloration in the presence of hypochlorite bleach.

TABLE 2

Example or Comp Ex	biguanide	organic acid	bleach	Appearance	Surviving bacteria
Control	none	none	no	white	6E3
F	none	none	yes	white	7E3
G	none	1% citric	no	white	6E2
H	0.01%PHMB	none	yes	yellow	0
18	0.01%PHMB	1% citric	yes	white	0

Example 19

This example illustrates the durability of the antimicrobial activity to repeated laundering. Samples of polyester/cotton (65/35) woven material were treated and tested as in Example 18 after five repeated washes for 50 minutes at 45°C in a 0.2% w/w aqueous solution of sodium alkylethoxysulphonate. In this example, bleaching in the 3% aqueous solution of sodium hypochlorite was carried out for 20 minutes at 20-25°C. The results are given in Table 3 which shows that the polyester/cotton material withstands discolouration in the presence of bleach and retains microbiological activity even after 5 laundering cycles in the presence of an anionic surfactant.

TABLE 3

Example	Treatment	Surviving cells after 5 laundering	whiteness (%)
Control	none	3E7	89
I	2% PHMB	6E2	80
19	2% PHMB+ 1% citric	0	88

Example 20

Example 14 was repeated except that the cotton cloth was replaced by the same amount of a 35/65 cotton/polyethylene glycol terephthalate blend woven piece and the oxalic acid solution was 0.5% by weight. The results are given in Table 4 below.

Table 4

Example	Treatment	Appearance	Whiteness (%)
20	0.1% PHMB/ 0.5% oxalic acid	white	80.99
J	0.1% PHMB	yellow	70.69
Control		white	81.9

Example 21

White cotton woven pieces (250 parts) was immersed in a 0.1% aqueous solution of PHMB for 5 minutes at 20-25°C. The cotton piece was then removed and rinsed thoroughly with water. The treated cotton was then immersed in 0.5% aqueous solution of oxalic acid for 5 minutes at 20-25°C and again removed, squeezed, rinsed with water and dried. The

cotton was then padded with a 0.2% solution of a glycoluril resin containing an acid catalyst, squeezed through a pair of nip rollers to give 60% pick-up and finally dried and baked for 10 minutes at 140°C to cure the resin.

5 A similar cotton woven piece was prepared but omitting the oxalic acid treatment. A length of untreated cotton was used as control.

10 5cm² squares of the above cotton cloths (0.25 parts) were treated with sodium hypochlorite as described in Example 14 and the antimicrobial properties were assessed as described in Example 18. The results are given in Table 5 below after subjecting to 0, 5 and 10 washing cycles as described in Example 19.

Table 5

15

Example	Treatment	No. of Washes	Whiteness (%)	Surviving bacteria
21	0.1% PHMB	0	109	0
	0.5% oxalic acid	5	116	0
	0.2% glycoluril	10	126	0
K	0.1% PHMB	0	84.3	0
	0.2% glycoluril	5	91.6	3.4 E2
		10	101.9	1.7 E2
Control	None	0	97.4	4.3E2

20 Examples 22 to 24

White 35/65 cotton/polyethylene glycol terephthalate woven pieces (250 parts) were immersed in an aqueous solution of 0.4% PHMB for 5 minutes at 20-25°C. They were then removed, squeezed, rinsed in water and dried. Half of the pieces were then immersed in a 2% aqueous solution of citric acid for 5 minutes at 20-25°C and again removed, squeezed and rinsed in water.

25 After drying the treated pieces were padded through a 1% aqueous bath of a curable resin, squeezed between nip rollers to give 60% up take, dried and baked for 10 minutes at 140°C.

30 The treated fabrics were then immersed in sodium hydrochlorite as described in Example 1. The protection against yellowing conferred by the citric acid is recorded in Table 6 below.

Table 6

Example	Treatment	Citric Acid	Whiteness (%)
Control	-	-	90
L	0.4% PHMB	-	82
M	0.4% PHMB 1% epoxy resin	-	82
22	0.4% PHMB 1% epoxy resin	2%	90
0	0.4% PHMB 1% melamine resin	-	85
23	0.4% PHMB 1% melamine resin	2%	88
P	0.4% PHMB 1% urethane resin	-	85
24	0.4% PHMB 1% urethane resin	2%	90

Example 25




Example 15 was repeated except that the PHMB was replaced by the same amount of chlorhexidine digluconate and the strong organic acid used was a 0.5% aqueous solution of malonic acid. The results are given in Table 7 below.

Table 7

Example	Treatment	Whiteness (%)
25	0.1% chlorhexidine 0.5% malonic acid	83
Q	0.1% chlorhexidine	10.9
Control	-	97.1


CLAIMS

1. A method of treating a textile material to inhibit microbial growth which comprises applying to the textile material a) an oligo- or polymeric biguanide or salt thereof with an inorganic acid or an organic acid having a pK value above 4.5 and b) a strong organic acid having a pK value below 4.5 and free from any aliphatic or oxyalkylene chain containing 12 or more carbon atoms.
2. A method according to claim 1 wherein the strong organic acid has a pK value from 3.1 to 0.5.
3. A method according to either claim 1 or claim 2 wherein the biguanide contains at least two biguanide units of formula
4. A method according to claim 3 wherein the biguanide is a compound of formula IIa or IIb or III



wherein n is 4 to 15.

5. A method according to any one of claims 1 to 4 wherein the strong organic acid has the formula IV



wherein


R is halogen, C₁₋₆-alkyl, C₁₋₆-alkenyl, substituted C₁₋₆-alkyl, phenyl, substituted phenyl, nitrile, carboxy, a group OR³ or a group R³CO.

R¹ and R² are, independently, hydrogen, halogen, amino, substituted amino, hydroxy, C₁₋₆-alkyl, substituted C₁₋₆-alkyl or R and R¹ together with the carbon atom to which they are attached form an alicyclic or heterocyclic ring; and

R³ is C₁₋₆-alkyl, substituted C₁₋₆-alkyl, phenyl or substituted phenyl;

provided that R, R¹ and R² are selected to give a pK value below 4.5.

6. A method according to any one of claims 1 to 4 wherein the strong organic acid has the formula V



wherein

R⁴ is hydrogen, C₁₋₆-alkyl, substituted C₁₋₆ alkyl, C₁₋₆-alkenyl, phenyl substituted phenyl or -COOH; and

R⁵ and R⁶ are, independently, hydrogen, C₁₋₄-alkyl or substituted C₁₋₄-alkyl.

7. A method according to any one of claims 1 to 4 wherein the strong organic acid has the formula VI




wherein

R⁷ is phenyl, substituted phenyl or the group -COOH.

8. A method as claimed in any one of claims 1 to 4 wherein the acid is malonic, maleic, citric or oxalic acid.

9. A method as claimed in any one of claims 1 to 8 wherein the textile material is cellulose or a blend thereof.

10. A salt of a biguanide of formula III



wherein n is 4 to 15 and a strong organic acid having a pK value below 4.5 and free from any aliphatic or oxyalkylene chain containing 12 or more carbon atoms.

- 5 11. A textile material treated with a) an oligo- or polymeric biguanide or salt thereof with an inorganic acid or an organic acid having a pK value above 4.5 and b) a strong organic acid having a pK value below 4.5 and free from any aliphatic or oxyalkylene chain containing 12 or more carbon atoms.

INTERNATIONAL SEARCH REPORT

Int. Appl. No.
PCT/GB 94/02184

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 D06M13/432 D06M16/00 A01N47/44 C07C279/26

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 D06M A01N C07C A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB,A,821 113 (IMPERIAL CHEMICAL INDUSTRIES LIMITED) 30 September 1959 see page 2, left column, line 77 - page 3, left column, line 55; claims; example 5 ---	1,3-5,9,11
X	BE,A,698 595 (IMPERIAL CHEMICAL INDUSTRIES LIMITED) 17 November 1967 see page 3, line 21 - line 23; claims; example 4 ---	1,3-5,11
X	US,A,5 141 803 (PREGOZEN) 25 August 1992 see column 3, line 43 - line 62 see column 4, line 14 - line 25 see column 4, line 63 - line 67; claims; example 1 ---	1-5,8-11
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *A* document member of the same patent family

Date of the actual completion of the international search

26 January 1995

Date of mailing of the international search report

08.02.95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Blas, V

INTERNATIONAL SEARCH REPORT

Int. Application No.
PCT/GB 94/02184

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 265 202 (UNILEVER PLC.) 27 April 1988 see page 2, line 63 - page 3, line 23; claims	1-9,11
X	---	10
X	DE,A,40 26 756 (TURNER GMBH) 27 February 1992 see claim 1	10
X	---	
X	EP,A,0 485 079 (IMPERIAL CHEMICAL INDUSTRIES LIMITED) 13 May 1992 see page 4, line 51 - page 5, line 13	10
X	---	
X	GB,A,2 202 443 (WR GRACE & CO.) 28 September 1988 see page 3, line 16 - page 4, line 8 see page 4, line 21 - page 5, line 4	10
A	---	
A	GB,A,2 187 097 (UNILEVER PLC.) 3 September 1987 see page 1, line 35 see page 1, line 49 - line 54 -----	1-11

INTERNATIONAL SEARCH REPORT

information on patent family members

Inter. natl Application No

PCT/GB 94/02184

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB-A-821113		NONE	
BE-A-698595	17-11-67	FR-A- 1545593 NL-A- 6707136	24-11-67
US-A-5141803	25-08-92	AU-B- 623906 AU-A- 3648289 JP-A- 2061000	28-05-92 04-01-90 01-03-90
EP-A-0265202	27-04-88	AU-B- 596875 AU-A- 7978587 US-A- 5000867	17-05-90 21-04-88 19-03-91
DE-A-4026756	27-02-92	NONE	
EP-A-0485079	13-05-92	AU-B- 646097 AU-A- 8604891 JP-A- 4264009	10-02-94 14-05-92 18-09-92
GB-A-2202443	28-09-88	NONE	
GB-A-2187097	03-09-87	NONE	